

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
27 November 2003 (27.11.2003)

PCT

(10) International Publication Number
WO 03/097927 A1

(51) International Patent Classification⁷: **D06M 16/00**,
C12N 11/08

(21) International Application Number: **PCT/PT02/00008**

(22) International Filing Date: **21 May 2002 (21.05.2002)**

(25) Filing Language: **English**

(26) Publication Language: **English**

(71) Applicant (for all designated States except US): **UNIVERSIDADE DO MINHO [PT/PT];** Largo do Paço,
P-4700-320 Braga (PT).

(72) Inventors; and

(75) Inventors/Applicants (for US only): **CAVACO PAULO, Artur [PT/PT];** Rua Coronel Albino Rodrigues, n° 25 - 3° E, P-4710-214 Braga (PT). **DOS SANTOS MARINHO DA SILVA, Carla, Joana [PT/PT];** Rua José António Cruz, n° 181 - 5° E.-Trás, P-4710 Braga (PT).

(74) Agent: **LUIS SILVA CARVALHO;** Rua Vitor Cordon, 14, P-1249-103 Lisboa (PT).

(81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

Published:

— with international search report

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: **TREATMENT OF ANIMAL HAIR FIBERS WITH MODIFIED PROTEASES**

(57) Abstract: A method of treating fibers of animal origin (wool from sheep, cashmere, rabbit, mohair, llama, goat, camel, among others), characterised in that it consists of bringing the fiber into contact with a solution of modified proteases, bonded or not to other substances, in order to increase its molecular weight and reduce its diffusion inside the fiber. It is intended that the cuticle of the fiber be the only accessible part to the protease attack, thus allowing an increase in the resistance to shrinkage and anti-felt finishing, in comparison with untreated material.

WO 03/097927 A1

DESCRIPTION

"TREATMENT OF ANIMAL HAIR FIBERS WITH MODIFIED PROTEASES"

Field of the invention

The cuticle layer of animal hair fibers presents a scaly structure when observed by microscopy. The felting or shrinkage of these fabrics is due to the overlapping of these scales that surround the cortex (inner part of the fiber), in wet processes with high mechanical agitation. The removal of the cuticle layer makes it possible to eliminate the tendency of the protein fibers of animal origin to shrink. One possibility of anti-felt treatment would be the application of proteolytic treatments for the removal of the cuticle layer. This kind of treatment has been extensively studied since the beginning of the 20th century, but without great achievements.

The reasons for this are primarily due to the following factors:

- Hair fibers of animal origin have a very variable composition, which depends on origin, race, climate and animal feeding. This diversity of animal fibers induces various susceptibilities to proteolytic treatments.
- More aggressive treatments to induce a uniform anti-felting behaviour in all the fibers consequently cause unacceptable loss of strength.
- Recent studies indicate that the lack of reproducibility of the proteolytic treatments and the degradations caused by such treatments are due to the diffusion of the enzymes inside the animal fibers.

Background to the invention

The most commonly used method to confer dimensional stability on articles made from animal hair fibers is the INS/CSIRO Chlorine/Hercosett, which comprises a strong acid chlorine treatment, followed by the application of a polymer resin. This process results in an increased degree of shrinking resistance, but has a number of drawbacks: poor feel, limited durability, difficulties in dyeing and, more importantly today, it generates environmentally damaging waste.

Several authors have suggested methods to reduce the shrinkage of animal fibers, such as wool for instance, which do not result in the release of substances that are harmful to the environment. Among such processes, there are the enzymatic ones, as well as benign chemical processes such as low-temperature plasma treatments. Plasma treatment is a dry process, which involves treating wool fiber material with electric gas discharges (so-called plasma). At present, there are serious obstacles, such as costs, compatibility and capacity, to large-scale commercialisation of a plasma treatment process.

Several enzymatic methods have been used in the treatment of wool. The patent JP-A 51099196 describes a process to treat wool fabrics with alkaline proteases. The patent JP-A 3213574 describes a method for the treatment of wool with transglutaminase or a solution having this enzyme. The patent US 6051033 describes a method of wool or wool fiber treatment with a proteolytic enzyme and transglutaminase. WO 98/27264 describes a method to reduce the shrinking of wool that consists of bringing the fiber samples into contact with a solution of peroxidase or oxidase under adequate conditions for the enzymatic reaction with wool. The patent US 6099588 relates a method to improve shrink resistance that may result in improvements in feel, appearance

- 3 -

and felting, among others, by the application of proteolytic enzymes in an aqueous solution, after treatment with an alkaline solution containing alcohol. The patent US 5.529.928 refers to a process for obtaining wool with anti-felt finishing, a soft feel and with shrink resistance using an initial chemical oxidation followed by a treatment with protease and warming. The patent EP 134267 uses a similar process, treating the fiber with proteolytic enzymes in the presence of salt, after the initial oxidative treatment. The patent EP 3.58386 describes a method of wool treatment that consists of a proteolytic treatment and one of, or both, an oxidative treatment (such as NaOCl) and treatment with polymer.

The necessity of establishing environmentally friendly (Eco-friendly) methods with better performances than the industrial processes currently used, creates a need for new processes that give a good shrink resistance, softness, appearance and anti-pilling behaviour. Therefore, a new methodology of enzymatic treatment of animal hair fibers is presented here.

Summary of the invention

This invention relates to a new enzymatic process of animal hair fiber treatment, in which the proteases are chemically modified in order to increase their molecular weight and therefore reduce their diffusion inside the fiber. The cuticle will be the only accessible part to the proteolytic attack, which allows for the improvement of one or more wool properties, including their felting and shrinking, without damaging the fiber's interior.

The methodologies used to increase the molecular weight of the enzymes are based on the utilisation of a soluble polymer with hydroxyl groups activated with γ -aminopropyltriethoxysilane and/or glutaraldehyde. The

glutaraldehyde may subsequently bind to another polymer chain, forming a polymeric net, or to an available protein NH_2 group.

Detailed Description and Examples

The method consists of the treatment of the proteic material with a solution of modified proteolytic enzymes. Commercially available proteases from Sigma (*Subtilisin* kind) were used.

Immobilisation was performed on a soluble polymer, polyvinyl alcohol (Sigma), of average molecular weight 70000–100000, using glutaraldehyde (Aldrich), γ -aminopropyltriethoxysilane and/or borax (Sigma) and polyethylenglycol (Sigma) of 10000 of average molecular weight.

The polymer at 6% (w/v) solution in distilled water was dissolved with warming and stirring, activated, and was then added to a 2% (v/v) glutaraldehyde solution. This solution was kept under stirring at room temperature, for 2 hours. After this time, the solution was dialysed in 0.1 M pH 5.0 acetate buffer for 24 hours and then in 0.05 M pH 3.95 acetate buffer for 20 hours.

The enzymatic preparation in the desired concentration was added to the resulting solution, together with PEG (1.25%) and borax (0.05 $\mu\text{g/mL}$) in 0.1 M pH 5.0 acetate buffer, and kept under stirring for 8 hours at room temperature. This solution was kept at 4°C until use. The immobilisation procedure did not cause any significant loss in activity.

Example 1:**Treatment of pure wool fabric with proteases:**

Samples of pure merino wool fabric (like animal hair fiber) of about 12 cm x 12 cm (of about 3 grams each) were placed in a recipient containing a solution of proteases being chemically modified or not, in a relation of 1/20 (w/v). The treatment was performed at 37°C, for periods of time ranging from 4 to 48 hours. The samples were removed from the solution, washed and air-dried. They were then subjected to tests to evaluate possible damage caused during the treatment.

To evaluate the quality of the fabric and the degree of damage caused in the wool treatment process, a qualitative test based on Garner (Garner W., *Textile Laboratory Manual*, vol. 5 - Fibres, 3rd Edition, 1967) was used. It was verified that the modified proteases did not induce fiber degradation when compared with free proteases. The control treatment itself (0.10 M pH 7.5 acetate buffer) presents a level of degradation higher than that presented by the fibers treated with modified enzymes.

The tendency of the fabrics to shrink was verified by washing the fabrics (11 x 6 cm) three times in distilled water containing 50 µL of a wetting agent for 60 minutes, at 50°C and 20 rpm, and the shrinkage was measured by the variation of the specimen dimensions. It was verified that only the enzymatically treated fabrics did not induce a significant shrinkage.

A panel of 5 experts evaluated the feel and appearance of the wool fabric and verified an increase in the properties of the protease treated fabrics compared to the control fabric.

Example 2:Treatment of pure wool yarns with proteases:

Similar studies were conducted in yarns of merino wool using the following parameters: samples of pure wool yarn were placed in a recipient containing a solution of proteases being chemically modified or not, in a ratio of 1/20 (w/v). The treatment was conducted at 37°C, for periods of time ranging from 4 to 48 hours. The samples were removed from the solution, washed and air-dried. They were then subjected to tests to evaluate possible damage caused during treatment.

To evaluate the yarn quality and the degree of damage caused in the treatment process of this fiber, a qualitative test based on Garner (Garner W., *Textile Laboratory Manual*, vol. 5 - Fibres, 3rd Edition, 1967) was used. It was verified that the modified protease treatment does not induce degradation when compared with free protease treatment. The control treatment (10 mM pH 7.5 acetate buffer) presented a level of degradation higher than that presented by the fibers treated with the modified enzymes. Tensile strength tests were performed on wool yarns, and it was verified that only the yarns treated with free proteases induced a significant loss of strength.

The tendency to shrink was verified by washing the wool yarns three times in distilled water having 50 µL of a wetting agent for 60 minutes, at 50°C and 20 rpm, and shrinkage was quantified by the visual verification of yarn felting. It was verified that only the enzymatically treated yarns did not induce felting.

A panel of 5 experts evaluated the appearance of the yarns and

- 7 -

verified a better appearance of the yarns treated with proteases, compared to the control yarns.

CLAIMS

1. A method of treating fibers of animal origin (wool from sheep, cashmere, rabbit, mohair, llama, goat, camel, among others), characterised in that it consists of bringing the fiber into contact with a solution of modified proteases, bonded or not to other substances, in order to increase its molecular weight and reduce its diffusion inside the fiber. It is intended that the cuticle of the fiber be the only accessible part to the protease attack, thus allowing an increase in the resistance to shrinkage and anti-felt finishing, in comparison with untreated material.
2. The method according to claim 1, characterised in that it consists of the treatment of the fibers simultaneously with a proteolytic enzyme and transglutaminase or a proteolytic enzyme and glutaraldehyde.
3. The method according to claim 1, characterised in that the proteolytic enzyme is of bacterial origin.
4. The method according to claim 1, characterised in that the proteolytic enzyme is a serine protease.
5. The method according to claims 1 and 4, characterised in that the serine protease is a *Subtilisin Carlsberg*.
6. The method according to claim 1, characterised in that the amount of protease used per Kg of wool, fiber or hair is in the range of 1 to 1000 g.

- 9 -

7. The method according to claim 1, characterised in that the transglutaminase is derived from Streptovercillium sp.

8. The method according to claim 1, characterised in that a treatment bath with recoverable and reusable protease solution is used, thus reducing the costs of the treatment and the production of effluents, with concomitant savings in water consumption.

9. The method according to claim 1, characterised in that soluble polymers in aqueous solutions, such as polyvinyl alcohol (and/or polymers with hydroxyl groups), are used as supports in the chemical modification of proteases, without restrictions.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/PT 02/00008

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 D06M16/00 C12N11/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 7 D06M C12N

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the International search (name of data base and, where practical, search terms used)

EPO-Internal, WPI Data, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 99 60200 A (NOVO NORDISK BIOCHEM INC) 25 November 1999 (1999-11-25) page 2, line 22 -page 3, line 6 page 8, line 3 - line 25 page 10, line 23 -page 11, line 7 examples 1,6	1-7
X	DATABASE WPI Section Ch, Week 199509 Derwent Publications Ltd., London, GB; Class A35, AN 1995-064089 XP002229518 & JP 06 341067 A (OSAKA PREFECTURE), 13 December 1994 (1994-12-13) abstract	1,6,8,9

-/--



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *G* document member of the same patent family

Date of the actual completion of the international search

31 January 2003

Date of mailing of the international search report

11/02/2003

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Flocco, M

INTERNATIONAL SEARCH REPORT

International Application No
PCT/PT 02/00008

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 00 50686 A (MCDEVITT JASON PATRICK ;NOVO NORDISK BIOCHEM INC (US); XIANGHONG C) 31 August 2000 (2000-08-31) cited in the application page 3, line 24 -page 4, line 6 ---	1-9
A	US 4 970 156 A (BROUN GEORGES ET AL) 13 November 1990 (1990-11-13) column 2, line 63 -column 3, line 43 column 10, line 13 - line 19 example 9 -----	1-9

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/PT 02/00008

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
WO 9960200	A	25-11-1999	US 6051033 A	18-04-2000
			AU 3986199 A	06-12-1999
			AU 4074699 A	06-12-1999
			CN 1301320 T	27-06-2001
			CN 1301321 T	27-06-2001
			EP 1088128 A1	04-04-2001
			EP 1082484 A1	14-03-2001
			JP 2002515555 T	28-05-2002
			PL 344294 A1	22-10-2001
			PL 344338 A1	05-11-2001
			TR 200003419 T2	21-03-2001
			TR 200003436 T2	20-04-2001
			WO 9960199 A1	25-11-1999
			WO 9960200 A1	25-11-1999
			US 6140109 A	31-10-2000
JP 6341067	A	13-12-1994	NONE	
WO 0050686	A	31-08-2000	US 6099588 A	08-08-2000
			AU 3004900 A	14-09-2000
			CN 1348519 T	08-05-2002
			EP 1157155 A1	28-11-2001
			NZ 513647 A	28-09-2001
			WO 0050686 A1	31-08-2000
US 4970156	A	13-11-1990	FR 2028702 A6	16-10-1970
			FR 2035774 A6	24-12-1970
			CA 953214 A1	20-08-1974
			CH 538003 B	31-01-1973
			CH 453269 A	31-01-1973
			CH 564031 A5	15-07-1975
			DE 1915970 A1	09-10-1969
			FR 2107801 A6	12-05-1972
			FR 1604982 A	26-06-1972
			GB 1257263 A	15-12-1971
			JP 51012712 B	21-04-1976
			US 4464468 A	07-08-1984
			US 4004979 A	25-01-1977